

(19)



(11)

**EP 2 174 777 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:

**14.04.2010 Bulletin 2010/15**

(51) Int Cl.:

**B32B 3/06 (2006.01)**

**B32B 7/08 (2006.01)**

**E04C 2/34 (2006.01)**

(21) Application number: **09166303.9**

(22) Date of filing: **24.07.2009**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR**

Designated Extension States:

**AL BA RS**

• **Piimat Oy**

**01260 Vantaa (FI)**

(72) Inventors:

• **Sevon, Jukka**

**21600, Pargas (FI)**

• **Hyttinen, Matti**

**02200, Espoo (FI)**

• **Luoma, Rauno**

**64700, Teuva (FI)**

(30) Priority: **31.07.2008 FI 20085755**

(71) Applicants:

• **Paroc Oy Ab**

**01300 Vantaa (FI)**

• **Betoniluoma Oy**

**64700 Teuva (FI)**


(74) Representative: **LEITZINGER OY**

**Tammasaarekatu 1**

**00180 Helsinki (FI)**

(54) **Sandwich concrete panel and method of making the same**

(57) The invention relates to a sandwich concrete panel, which includes a body-forming internal leaf (1), an insulation layer (2) of mineral wool installed thereon, and an outer leaf (3) installed on top of the insulation layer. The mineral wool insulation layer (2) is lamellar in structure, in which lamellae (2b) the fibers of mineral wool lie in an orientation substantially perpendicular to the surfaces of the internal and outer leaves. The outer leaf (3) is constructed in fiberplastic-reinforced concrete and the internal leaf (1) as well as the outer leaf (3) are secured to each other by push-through trusses (4b) extending through the insulation layer (2). The invention relates also to a method of making a sandwich concrete panel.



**Fig. 3b**

**EP 2 174 777 A1**